Specification of Thermoelectric Module TES1-01714

Description

The 17 couples, 5.9mm × 20mm size module is a single stage module which is made of our high performance ingot to achieve superior cooling performance and 70°C or larger delta Tmax, is designed for superior cooling and heating applications. Beyond the standard below, we can design and manufacture the custom made module according to your special requirements.

Features

- No moving parts, no noise, and solid-state
- Compact structure, small in size, light in weight
- Environmental friendly
- RoHS compliant
- Precise temperature control
- Exceptionally reliable in quality, high performance


Application

- Food and beverage service refrigerator
- Portable cooler box for cars
- Liquid cooling
- Temperature stabilizer
- CPU cooler and scientific instrument
- Photonic and medical systems

Performance Specification Sheet

Th (°C)	27	50	Hot side temperature at environment: dry air, N ₂	
DT _{max} (°C)	70	79	Temperature Difference between cold and hot side of the module when cooling capacity is zero at cold side	
U _{max} (Voltage)	2.11	2.28	Voltage applied to the module at DT _{max}	
I _{max} (Amps)	1.5	1.5	DC current through the modules at DT _{max}	
Q _{Cmax} (Watts)	2.04	2.20	Cooling capacity at cold side of the module under DT=0 °C	
AC resistance (Ohms)	1.07	1.15	The module resistance is tested under AC	
Tolerance (%)	± 10		For thermal and electricity parameters	

Geometric Characteristics Dimensions in millimeters



Manufacturing Options

A. Solder:

1. T100: BiSn (Tmelt=138°C)

B. Sealant:

1. NS: No sealing (Standard)

2. T200: CuAgSn (Tmelt = 217° C)

2. SS: Silicone sealant

3. T240: SbSn (Tmelt = 240° C)

3. EPS: Epoxy sealant

C. Ceramics:

D. Ceramics Surface Options:

1. Alumina (Al₂O₃, white 96%)

1. Blank ceramics (not metalized)

2. Aluminum Nitride (AlN)

2. Metalized

Ordering Option


Suffix	Thiolmoss II (mm)	Flatness/ Parallelism	Lead wire length(mm)Standard/			
	Thickness H (mm)	(mm)Parallelism (mm)	Optional length			
TF	$0: 3.2 \pm 0.1$	0: 0.05/0.05	150±3/Specify			
TF	$1: 3.2 \pm 0.03$	1: 0.02/0.02	150±3/Specify			

Eg. TF01: Thickness 3.1 ± 0.1 (mm) and Flatness 0.02/0.02 (mm)


Specification of Thermoelectric Module

TES1-01714


Performance Curves at Th=27 °C




Performance Curves at Th=50 °C





Standard Performance Graph Qc= f(DT)





Standard Performance Graph V= f(DT)






Standard Performance Graph Qc = f(V)


Specification of Thermoelectric Module

TES1-01714


Performance Curves at Th=27 °C


Performance Curves at Th=50 °C





Standard Performance Graph COP = f(V) of DT ranged from 0 to 30 °C





Standard Performance Graph COP = f(V) of DT ranged from 40 to 60/70 °C

Remark: The coefficient of performance (COP) is the cooling power Qc/Input power ($V \times I$).

Operation Caution

- Cold side of the module sticked on the object being cooled
- Hot side of the module mounted on a heat radiator
- Operation below I_{max} or V_{max}
- Work under DC

Note: All specifications subject to change without notice.